

## **Technical Data Sheet**

## Fradiflex® metal water stop

**Fradiflex**® **metal water stop** consists of galvanised sheet steel with single or double-sided special coating.





Product	
Description	<b>Fradiflex</b> ® <b>metal water stop</b> consists of a galvanized steel sheet in different heights, with single or double-sided special coating. The special coating is protected with a foil.
	Fradiflex® metal water stop is available in different lengths.
Use	Fradiflex® metal water stop can be used to seal construction joints in in-situ concrete - at the wall-to-floor transition without concrete upstand, at the wall-to-ceiling or the floor-to-floor and wall-to-wall transition in building construction, civil engineering and structural engineering.
Characteristics/ benefits	Maximum allowable water pressure of 2 bar according to declaration of performance. Tested up to 5 bar.
Test (copies on re	quest)
Approval/	European approval (ETA-15/0914) of DIBt Berlin dated 7 March 2016
permission	Test certificate of the Technical University Munich for:
	<ul> <li>single or double-sided special coating Fradiflex® metal water stop (abP No: P-51-07-0084\002 dated 15.01.2018)</li> </ul>
	<ul> <li>single or double-sided special coating metal water stop Fradiflex® controlled crack joint element</li> <li>(abP-No.: P-51-07-0084\003 dated 30.08.2018)</li> </ul>
	Fire: Test certificate no. B18269 of the TU Munich dated 08.10.2018
	THE. Test sertificate field for biological of the TO Mutifiel dated 60.10.2010



Product details	
Design	<b>Fradiflex</b> ® <b>metal water stop</b> consists of a metal water stop with or without mounting bracket and is supplied in rolls or in strip form. The overlapping joints are bonded by the coating and secured with staples.
	The sheets have a special coating on one or both sides, which later bonds with the concrete.
	A thin foil covers the sheet or coating over the entire surface. The foil halves have a separating cut for later removal.
Packaging	Fradiflex® metal water stop is supplied as follows:
- uogg	- 25 m roll: 1 roll/box / 36 boxes per pallet or
	- 2.1 m straight pieces: 50 pcs/box
Storage	12 months after date of production at max. 35 °C protected from moisture.
Physical characteristics	<b>Fradiflex® metal water stop</b> is manufactured from a galvanized slit strip (DX51) i heights of 120 mm or 150 mm <sup>1</sup> . The sheet thickness is 0.6 mm and is cut into rolls of 25 m or straight pieces of 2.1 m length. The product is temperature-resistant from - 30°C to + 70°C and can be processed from - 15°C to + 50°C <sup>2</sup> .
	The material for the special coating consists of an elastomeric plastic, free of formaldehydes. The layer thickness of the black special coating is approx. 0.2 mm (single or double-sided). The coating is free of mercury, lead, cadmium and chromium (VI) in accordance with Directive 94/62/EG. According to EN ISO 11890-2:2001, the content of volatile organic hydrocarbons (VOC`s) is less than 0.3 %, according to regulation CH814.018 = 0 %.
	The protective film is made of polypropylene. It protects the coating from dirt, dust and, while pouring, from unintentional concrete splashes. After removing the film, the coating should not be exposed to weather for more than 7 days.
Disclaimer / Notes:	All technical data stated in this TDS are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.  Recommendations with regard to product application given in the present technical data sheet for practical assistance of product users are based on our experience and our present scientific and practical body of knowledge. These recommendations, however, are given without engagement and do not establish a contractual relationship or subsidiary duties. These recommendations do not relieve users of their liability and of their own responsibility to test, whether our product is adequate for the intended purpose of application. Please refe to the latest edition of this Technical Data Sheet on our web presence www.maxfrank.com

## Max Frank GmbH & Co. KG

Mitterweg 1 | 94339 Leiblfing | Germany | Telephone +49 9427 189-0 | Fax +49 9427 1588 | info@maxfrank.com

 $<sup>^{\</sup>rm 1}$  Version with height 80 mm must be checked separately for installation  $^{\rm 2}$  Irrespective of this the concrete must be protected from frost during and after pouring!